



Technical Bulletin

PLSF 70342 Ral 7012 Basalt Grey

Description: *PLSF 70342, Ral 7012 Basalt Grey* is a thermosetting Polyester-TGIC powder coating and is designed for exterior durability, and will meet or exceed AAMA 2603. This product has been formulated for exceptionally high gloss and flow.

**Typical
Powder Properties**

Specific Gravity (ASTM D5965-96, C)	1.52±0.05
Theoretical Coverage	126sq.ft/lb./mil

**Typical
Physical Properties:**

Film Thickness	2.0-3.0 mil
Gloss 60°angle (ASTM D-523-89)	86-96 (visual)
Hardness (ASTM D-3363-92A)	2H
Flexibility (ASTM D-1737-89)	1/4-1/8 inch
Adhesion (ASTM D-3359-95A)	5B (100%)
Impact Direct/Indirect (ASTM D-2794-93)	120/120 in-lbs.
Salt Spray (ASTM B117, 1000 hrs, Bonderite 1000 panel)	Rating 7 (creepage)
Salt Spray (ASTM B117, 3000 hrs, Alodine panel)	Rating 7 (creepage)

Application Data: *PLSF 70342, Ral 7012 Basalt Grey* is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kV.

Cure Schedule: *PLSF 70342, Ral 7012 Basalt Grey* can be cured in a direct or indirect gas convection oven, an electric oven, or an Infrared. A combination of any of these ovens is also suitable.

Standard Cure: 10 minutes @ 340°F Peak Metal Temperature

Storage: *PLSF 70342, Ral 7012 Basalt Grey* should be stored at temperatures below 80°F, in a dry area away from any heat source.

Notes: All tests were performed on B-1000 panels with a nominal film thickness of 2.0-3.0 mils. Please refer to the SDS for safety information.

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.