



Technical Bulletin

PLSS 10029 Semi Gloss Black

Description:	PLSS 10029, Semi Gloss Black is a thermosetting Polyester-TGIC powder coating and designed for interior and exterior durability.	
Typical Powder Properties	Specific Gravity (ASTM D5965-96, C)	1.57±0.03
	Theoretical Coverage	122 sq.ft/lb./mil
	Mass loss during the cure (ASTM D3451-92)	<1.0%
Typical Physical Properties:	Film Thickness	1.8-3.0 mil
	Gloss 60°angle (ASTM D-523-89)	50-60
	Hardness (ASTM D-3363-92A)	H-2H
	Flexibility (ASTM D-1737-89)	1/8 inch
	Adhesion (ASTM D-3359-95A)	5B (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	160/160 in-lbs*,
	Salt Spray (ASTM B117, 1000 hrs., B-1000 panel)	Rating 7 (creepage)
	Salt Spray (ASTM B117, 1500 hrs., Alodine panel)	Rating 7 (creepage)
*no loss of adhesion		
Application Data:	PLSS 10029, Semi Gloss Black is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kV.	
Cure Schedule:	PLSS 10029, Semi Gloss Black can be cured in a direct or indirect gas convection oven, an electric oven, or an Infrared. A combination of any of these ovens is also suitable.	
	Standard Cure:	10 minutes @ 340°F Peak Metal Temperature
Storage:	PLSS 10029, Semi Gloss Black should be stored at temperatures below 80°F, in a dry area away from any heat source.	
Notes:	All tests were performed on Alodine panels with a nominal film thickness of 2.0-3.0 mils. Please refer to the MSDS for safety information.	

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.