



Technical Bulletin

SLFL 41939 Low Cure Bronze Texture

Description:	SLFL 41939, L/C Bronze Texture is a thermosetting Super Polyester-TGIC powder coating and designed for excellent exterior durability. When properly applied this product will meet or exceed the AAMA 2604-5 specification.	
Typical Powder Properties	Specific Gravity (ASTM D5965-96, C)	1.78+/-0.05
	Theoretical Coverage	108 sq./lb./mil
Typical Physical Properties:	Film Thickness	2.0-3.0 mil
	Gloss 60°angle (ASTM D-523-89)	10-20 (visual)
	Hardness (ASTM D-3363-92A)	2H
	Flexibility (ASTM D-1737-89)	¼-1/8 inch
	Adhesion (ASTM D-3359-95A)	5B (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	80/80 in-lbs.
	Salt Spray (ASTM B117, 1000 hrs, Bonderite 1000 panel)	Rating 7 (creepage)
	Salt Spray (ASTM B117, 3000 hrs, Alodine panel)	Rating 7 (creepage)
Application Data:	SLFL 41939, L/C Bronze Texture is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kV.	
Cure Schedule:	SLFL 41939, L/C Bronze Texture can be cured in a direct or indirect gas convection oven, an electric oven, or an Infrared. A combination of any of these ovens is also suitable.	
	Standard Cure:	10 minutes @ 325°F Peak Metal Temperature
Storage:	SLFL 41939, L/C Bronze Texture should be stored at temperatures below 80°F, in a dry area away from any heat source.	
Notes:	All tests were performed on B-1000 iron phosphated and Alodine panels with a nominal film thickness of 2.0-3.0 mils. Please refer to the MSDS for safety information.	

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.