



Technical Data Sheet

HLSF 90246 PC073 Clear

Description: *HLSF90246, PC073 Clear* is a thermosetting powder coating based on a blend of epoxy and polyester. Hybrids are designed for interior applications where exterior durability is not required.

Typical Applications: Decorative finishes

Typical Physical Properties:	Film Thickness (ASTM D)	2.0 – 3.0+ mil
	Gloss 60°angle (ASTM D-523-89)	90+
	Hardness (ASTM D-3363-92A)	2H
	Flexibility (ASTM D-1737-89)	1/8 inch
	Adhesion (ASTM D-3359-95A)	5B (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	up to 160 in-lbs
	Exterior Durability	Poor
	Chemical Resistance	Poor
	Salt Spray (ASTM B117)	1000Hrs < 1/8"
	Specific Gravity	1.22±0.05

Application Data: *HLSF90246, PC073 Clear* is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kv. Hybrids can also be formulated for tribo or fluid bed application upon request.

Cure Schedules: *HLSF90246, PC073 Clear* can be cured in a direct or indirect gas convection oven, an electric oven, or an Infrared. A combination of any of these ovens is also suitable.

Standard Cure: 10 Minutes @ 340°f Peak Metal Temperature

Storage: Product should be stored at temperatures below 80°f, in a dry area away from any heat source.

Notes: All tests were performed on Bonderite 1000, iron phosphated panels with a nominal film thickness of 2 mils. Please refer to the MSDS for safety information.

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.

3601 North Interstate 35
Gainesville
Texas 76240
Tel. (940) 668 1062
Fax. (940) 668 1061
www.ifscos.com Email: info@ifscos.com