



Technical Bulletin

HRSF 73338 Robust Primer

Description:	<i>HRSF 73338, Robust Primer</i> is a thermosetting Polyester-Epoxy powder coating and modified to provide excellent chemical resistance and corrosion protection and for the substrates where out-gassing is a problem, such as castings or galvanizing.	
Applications:	Automotive Aluminum and Steel wheels and general industrial applications	
Typical Powder Properties:	Specific Gravity (ASTM D5965-96, C)	1.54±0.05
	Theoretical Coverage	125 sq./lb./mil
	Mass loss during the cure (ASTM D3451-92)	<1.0%
Typical Physical Properties:	Film Thickness	2.0-3.0 mil
	Gloss 60°angle (ASTM D-523-89)	80-90
	Hardness (ASTM D-3363-92A)	2H-3H
	Flexibility (ASTM D-1737-89)	1/8 inch
	Adhesion (ASTM D-3359-95A)	5B (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	160/160 in-lbs.
	Salt Spray (ASTM B117, 2000 hrs, Bonderite 1000 panel)	Rating 7 (creepage)
Application Data:	<i>HRSF 73338, Robust Primer</i> is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kV.	
Cure Schedule:	<i>HRSF 73338, Robust Primer</i> can be cured in a direct or indirect gas convection oven, an electric oven, or an Infrared. A combination of any of these ovens is also suitable with air-temperatures not exceeding 420°F. It should be partially cured using the recommended stoving schedules, before application of the topcoat. The object temperature must not below 260°F or above 420°F.	
	Standard Cure:	9 minutes @ 400°F Peak Metal Temperature 14 minutes @ 380°F Peak Metal Temperature
Storage:	<i>HRSF 73338, Robust Primer</i> should be stored at temperatures below 80°F, in a dry area away from any heat source.	
Notes:	All tests were performed on Bonderite 1000, Iron Phosphate panels with a nominal film thickness of 2.0-3.0 mils. Please refer to the SDS for safety information.	

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.