



Technical Bulletin

PRFL 80862 White Texture

Description: *PRFL 80862, White Texture* is a thermosetting Polyester-TGIC powder coating. This product is designed for interior or exterior applications.

Typical Powder Properties	Specific Gravity (ASTM D5965-96, C)	1.65±0.03
	Theoretical Coverage	116 sq.ft/lb./mil
	Mass loss during the cure (ASTM D3451-92)	<1.0%

Typical Physical Properties:	Film Thickness	2.0-4.0 mil
	Gloss 60°angle (ASTM D-523-89)	5-15
	Hardness (ASTM D-3363-92A)	H-2H
	Flexibility (ASTM D-1737-89)	1/8inch
	Adhesion (ASTM D-3359-95A)	5B (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	160/160 in-lbs
	Diffuse Reflectance, Tristim, Y (ASTM E308-96)-D65	90-91at 3.0 mil*

Application Data: *PRFL 80862, White Texture* is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kV.

Cure Schedule: *PRFL 80862, White Texture* can be cured in a direct or indirect gas convection oven, an electric oven, or an Infrared. A combination of any of these ovens is also suitable.

Standard Cure: 10 minutes @ 400°F Peak Metal Temperature

Storage: *PRFL 80862, White Texture* should be stored at temperatures below 80°F, in a dry area away from any heat source.

Notes: All tests were performed on Bonderite 1000, Iron Phosphate panels with a nominal film thickness of 2.0-3.0 mils (* Minimum thickness). Please refer to the MSDS for safety information.

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.