



## Technical Bulletin

### PRMF 97217 Dormant Green Bonded

**Description:** *PRMF 97217, Dormant Green Bonded* is a thermosetting modified Polyester powder coating and designed for interior and exterior durability. When properly applied this product will meet or exceed the AAMA 2603 specification.

<b>Typical Powder Properties</b>	Specific Gravity (ASTM D5965-96, C)	1.21+/-0.05
	Theoretical Coverage	159 sq./lb./mil
<b>Typical Physical Properties:</b>	Film Thickness	2.0-3.0 mil
	Gloss 60'angle (ASTM D-523-89)	Visual
	Hardness (ASTM D-3363-92A)	2H
	Flexibility (ASTM D-1737-89)	¼-1/8 inch
	Adhesion (ASTM D-3359-95A)	5B (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	120/120 in-lbs.
	Salt Spray (ASTM B117, 1000 hrs, Bonderite 1000 panel)	Rating 7 (creepage)
Salt Spray (ASTM B117, 2000 hrs, Alodine panel)	Rating 7 (creepage)	

**Application Data:** *PRMF 97217, Dormant Green Bonded* is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kV.

**Cure Schedule:** *PRMF 97217, Dormant Green Bonded* can be cured in a direct or indirect gas convection oven, an electric oven, or an Infrared. A combination of any of these ovens is also suitable.

**Standard Cure:** 10 minutes @ 400°F Peak Metal Temperature

**Storage:** *PRMF 97217, Dormant Green Bonded* should be stored at temperatures below 80°F, in a dry area away from any heat source.

**Notes:** All tests were performed on B-1000 iron phosphated panels with a nominal film thickness of 2.0-3.0 mils. Please refer to the MSDS for safety information.

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.