



Technical Bulletin

PRSF 61288 Wet Red Smooth

Description: *PRSF 61288, Wet Red Smooth* is a thermosetting powder coating based on a blend of Polyester-TGIC for exterior and interior applications.

Typical Powder Properties	Specific Gravity (ASTM D5965-96, C)	1.35±0.05
	Theoretical Coverage	142 sq./lb./mil
	Mass loss during the cure (ASTM D3451-92)	<1.0%

Typical Properties:	Film Thickness (ASTM D)	2.0-3.0+ mil
	Gloss 60'angle (Visual)	90+
	Hardness (ASTM D-3363-92A)	H-2H
	Flexibility (ASTM D-1737-89)	1/8 inch
	Adhesion (ASTM D-3359-95A)	5B (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	160/160 in-lbs.
	Salt Spray (ASTM B117, B1000 panels, 1000 hrs.)	ASTM Ratings #7

Application Data: *PRSF 61288, Wet Red Smooth* is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kv. Hybrids can also be formulated for tribo or fluid bed application upon request.

Cure Schedules: *PRSF 61288, Wet Red Smooth* can be cured in a direct or indirect gas convection oven, an electric oven, or an Infra red. A combination of any of these ovens is also suitable.

Standard Cure: 10 Minutes @ 400°F Peak Metal Temperature

Storage: *PRSF 61288, Wet Red Smooth* should be stored at temperatures below 80°F in a dry area away from any heat source.

Notes: All tests were performed on Bonderite 1000, iron phosphated panels with a nominal film thickness of 2 mils. Lower gloss levels may require higher cure temperatures or longer dwell times. Please refer to the SDS for safety information.

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.