



Technical Bulletin

PLSF 20278 RAL 5008, Grey Blue

Description: *PLSF 20278, RAL 5008 Grey Blue* is a thermosetting Polyester-TGIC powder coating and designed for interior and exterior durability.

Typical Powder Properties	Specific Gravity (ASTM D5965-96, C)	1.52±0.05
	Theoretical Coverage	126.5 sq.ft/lb./mil
	Shelf life (at below 80°F in 50% humidity)	18 months

Typical Physical Properties:	Film Thickness	2.0-3.5 mil
	Gloss 60°angle (ASTM D-523-89)	80+
	Hardness (ASTM D-3363-92A)	H-2H
	Flexibility (ASTM D-1737-89)	1/8 inch
	Adhesion (ASTM D-3359-95A)	5B (100%)
	Impact Direct/Indirect (ASTM D-2794-93)	160/160 in-lbs.
	MEK Cure Test (ASTM D4752 or D5402, 25 drs)	See below notes*
	Salt Spray (ASTM B117, 1000 hrs, Bonderite 1000 panel)	Rating 7 (creepage)
Salt Spray (ASTM B117, 2000 hrs, Alodine panel)	Rating 7 (creepage)	

Application Data: *PLSF 20278, RAL 5008 Grey Blue* is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kV.

Cure Schedule: *PLSF 20278, RAL 5008 Grey Blue* can be cured in a direct or indirect gas convection oven, an electric oven, or an Infrared. A combination of any of these ovens is also suitable.

Standard Cure: 10 minutes 340F Peak Metal Temperature

Storage: *PLSF 20278, RAL 5008 Grey Blue* should be stored at temperatures below 80°F, in a dry area away from any heat source.

Notes: All tests were performed on Bonderite 1000, Iron Phosphate panels with a nominal film thickness of 2.0-3.0 mils. Please refer to the SDS for safety information.

**slight pigment staining on the Q-Tip and loss of gloss after 25 double rubs is common.*

Revised on 10-03-2025

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.