



## Technical Bulletin

### SLSL 81491 93032943 L/C Kim Satin White

**Description:** *SLSL 81491, 93032943 L/C Kim Satin White* is a thermosetting Super Polyester-TGIC powder coating and designed for excellent exterior durability.

<b>Typical Powder Properties</b>	Specific Gravity (ASTM D5965-96, C)	1.55±0.05
	Theoretical Coverage	124 sq.ft/lb./mil
	Shelf life (at below 80°F in dry condition)	12 months

<b>Typical Physical Properties:</b>	Film Thickness	2.0-3.0 mil
	Gloss 60°angle (ASTM D-523-89)	60-70
	Hardness (ASTM D-3363-92A)	2H-3H
	Flexibility (ASTM D-1737-89)	1/4 inch
	Adhesion (ASTM D-3359-95A)	5B (100%)
	Pull off Adhesion (ASTM D4541)	>1000 PSI
	Impact Direct (ASTM D-2794-93, No loss of adhesion)	100/100 in-lbs
	Salt Spray (ASTM B117, 1000 hrs, Bonderite 1000 panel)	Rating 7 (creepage)
Salt Spray (ASTM B117, 3000 hrs, Alodine panel)	Rating 7 (creepage)	

**Application Data:** *SLSL 81491, 93032943 L/C Kim Satin White* is to be applied with a corona electrostatic powder spray gun at between 60kv – 100 kV.

**Cure Schedule:** *SLSL 81491, 93032943 L/C Kim Satin White* can be cured in a direct or indirect gas convection oven, an electric oven, or an Infrared. A combination of any of these ovens is also suitable.

**Standard Cure:** 10 minutes @ 360°F Peak Metal Temperature

**Storage:** *SLSL 81491, 93032943 L/C Kim Satin White* should be stored at temperatures below 80°F, in a dry area away from any heat source.

**Notes:** All tests were performed on B-1000 iron phosphated panels with a nominal film thickness of 3.0-4.0 mils. Please refer to the SDS for safety information.

Any recommendations contained herein or any information given by any IFS COATINGS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS COATINGS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision.